

HyGold P600N

Paraffinic Base Oil Marketing Specification

This severely hydrotreated paraffinic base oil provides excellent color stability and consistency. It passes the IP 346 labeling requirement.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, SUS at 100°F (37.8°C)	ASTM D2161	575	625	599
Viscosity, SUS at 210°F (98.9°C)	ASTM D2161			70.5
Viscosity, cSt at 40°C (104°F)	ASTM D445			114.8
Viscosity, cSt at 100°C (212°F)	ASTM D445			12.7
API Gravity, 60°F (15.6°C)	ASTM D1250			30.0
Specific Gravity, 60°F (15.6°C)	ASTM D4052			0.8761
Viscosity Index	ASTM D2270	95		103
Viscosity-Gravity Constant	ASTM D2501			0.800
Density, lbs/gal at 60°F	ASTM D1250			7.298
Molecular Weight	ASTM D2502			560
Flash Point, COC, °F (°C)	ASTM D92	446 (230)		487 (253)
Color, ASTM	ASTM D6045		4.0	L3.5
Pour Point, °F (°C)	ASTM D5949		16 (-9)	-5 (-21)
Cloud Point, °F (°C)	ASTM D5773			25 (-4)
Noack Volatility, wt%	ASTM D5800			7.58
Water Content	ASTM D7546M		PASS	PASS
Appearance	ASTM D4176M		PASS	PASS
Chemical Properties				
Acid Number, mg KOH/g	ASTM D664			0.01
Aniline Point, °F (°C)	ASTM D611			248 (120)
Sulfur, ppm	ASTM D7220			147
Clay-Gel, wt%	ASTM D2007			
Saturates				82.8
Health and Safety Properties				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1
FDA Regulation	21 CFR 178.3620 (C)		PASS	PASS

HyGold P600N is a product of Ergon - West Virginia, Inc.
September 17, 2021