

HyGold 40

Naphthenic Base Oil Marketing Specification

This severely hydrotreated naphthenic base oil is primarily used in the metalworking and compounder blending industries. It has a low pour point, a low odor level, excellent color, and resistance to discoloration by heat or ultraviolet light.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, SUS at 100°F (37.8°C)	ASTM D2161	31	46	38.4
Viscosity, SUS at 210°F (98.9°C)	ASTM D2161			31
Viscosity, cSt at 40°C (104°F)	ASTM D445	2	5	3.6
Viscosity, cSt at 100°C (212°F)	ASTM D445			1.5
API Gravity, 60°F (15.6°C)	ASTM D1250			31.4
Specific Gravity, 60°F (15.6°C)	ASTM D4052			0.8686
Density, lbs/gal at 60°F	ASTM D1250			7.234
Density at 15.6°C, g/cm ³	ASTM D1250			0.8678
Molecular Weight	ASTM D2502			242
Flash Point, COC, °F (°C)	ASTM D92	218 (103)		245 (118)
Flash Point, PMCC, °F (°C)	ASTM D93	200 (93)		228 (109)
Color, Saybolt	ASTM D6045	20		30
Pour Point, °F (°C)	ASTM D5950			-115 (-81)
Water Content	ASTM D7546M		PASS	PASS
Appearance	ASTM D4176M		PASS	PASS
Chemical Properties				
Acid Number, mg KOH/g	ASTM D664		0.05	0.01
Aniline Point, °F (°C)	ASTM D611	142 (61)	162 (72)	152 (66)
Sulfur, ppm	ASTM D5453			7
Health and Safety Properties				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1

HyGold 40 is a product of Ergon Refining, Inc.
February 26, 2024