

HyVolt II NG

Dielectric Fluid Marketing Specification

This inhibited dielectric fluid is produced from severely hydrotreated naphthenic crude oil to meet the specification requirements defined in ASTM D3487-24 standards, Type II. HyVolt products have very low pour points and excellent oxidation stability.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, cSt at 100°C	ASTM D445		3.0	2.4
Viscosity, cSt at 40°C	ASTM D445		12.0	9.8
Viscosity, cSt at 0°C	ASTM D445		76.0	64.2
Specific Gravity, 15°C/15°C	ASTM D4052		0.9100	0.8816
Flash Point, COC, °C	ASTM D92	145		157
Color, ASTM	ASTM D1500		0.5	L0.5
Pour Point, °C	ASTM D5950		-40	-57
Aniline Point, °C	ASTM D611	63		79
Interfacial Tension, 25°C, dynes/cm	ASTM D971	40		47
Visual Examination, 25°C	ASTM D1524	Clear & Bright		Clear & Bright
Electrical Properties				
Dielectric Breakdown at 60 Hz, Disk electrodes, kV	ASTM D877	30		42
Dielectric Breakdown at 60 Hz, VDE, kV (1.0-mm) gap	ASTM D1816	20		26
Dielectric Breakdown at 60 Hz, VDE, kV (2.0-mm) gap	ASTM D1816	35		47
Impulse Breakdown Voltage, kV at 25°C	ASTM D3300	145		>300
Power Factor at 60 Hz, 25°C, %	ASTM D924		0.05	0.004
Power Factor at 60 Hz, 100°C, %	ASTM D924		0.30	0.030
Gassing Tendency, µL/min	ASTM D2300		0	-5
Chemical Properties				
Oxidation Stability, 110°C	ASTM D2440			
72 hr: Sludge, % by mass			0.1	0.01
Total Acid Number, mg KOH/g			0.3	0.01
164 hr: Sludge, % by mass			0.2	0.01
Total Acid Number, mg KOH/g			0.4	0.01
Oxidation Stability (Pressure Vessel), minutes	ASTM D2112	195		306
Oxidation Inhibitor Content, wt%	ASTM D2668	0.15	0.30	0.27
Corrosive Sulfur	ASTM D1275	Noncorrosive		Noncorrosive
Water Content, ppm	ASTM D1533		35	12
Neutralization Number, mg KOH/g	ASTM D974		0.03	0.01
PCB Content, ppm	ASTM D4059	Not Detected		Not Detected
Furanic Compounds, µg/L	ASTM D5837		25	1
Health and Safety Properties (not an ASTM D3487 requirement)				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1
FDA Regulation	21 CFR 178.3620 (C)	PASS		PASS